

ENVIRONMENTAL PRODUCT DECLARATION

as per /ISO 14025/ and /EN 15804/

Owner of the Declaration	ICDLI aisbl – International Committee of the Decorative Laminates Industry
Programme holder	Institut Bauen und Umwelt e.V. (IBU)
Publisher	Institut Bauen und Umwelt e.V. (IBU)
Declaration number	EPD-ICL-20170154-CBE1-EN
Issue date	13.11.2017
Valid to	12.11.2022

Decorative High-Pressure Compact Laminates
**International Committee of the Decorative
Laminates Industry (ICDLI aisbl)**

www.ibu-epd.com / <https://epd-online.com>



General Information

International Committee of the Decorative Laminates Industry aisbl (ICDLI)

Programme holder

IBU - Institut Bauen und Umwelt e.V.
Panoramastr. 1
10178 Berlin
Germany

Declaration number

EPD-ICL-20170154-CBE1-EN

This Declaration is based on the Product Category Rules:

Laminates, 07.2014
(PCR tested and approved by the SVR)

Issue date

13.11.2017

Valid to

12.11.2022



Prof. Dr.-Ing. Horst J. Bossenmayer
(President of Institut Bauen und Umwelt e.V.)



Dr. Burkhard Lehmann
(Managing Director IBU)

High Pressure Compact Laminate

Owner of the Declaration

ICDLI aisbl – International Committee of the Decorative
Laminates Industry
Rue de la presse 4
1000 Brussels/Belgium
Headoffice:
Städelstraße 10
60596 Frankfurt am Main/Germany

Declared product / Declared unit

Decorative High-Pressure Compact Laminate (HPL)
according to /EN 438-4/ produced by ICDLI aisbl
members. The EPD applies to 1 m² of Compact
Laminate Panels without fire-retardant properties with
an average density of 1350 kg/m³.

Scope:

The applicability of this document is restricted to
Compact Laminates produced by member companies
of the Laminate Association ICDLI aisbl.
Data has been provided by 12 member Compact
producing companies of the ICDLI aisbl for the year
2016. These companies represent 80 % of the ICDLI
aisbl members. The production volume of these
companies contributes more than 45% to the
Decorative High-pressure Compact laminates
production in Europe.

The owner of the declaration shall be liable for the
underlying information and evidence; the IBU shall not
be liable with respect to manufacturer information, life
cycle assessment data and evidences.

Verification

The CEN Norm /EN 15804/ serves as the core PCR

Independent verification of the declaration
according to /ISO 14025/

☐ internally ☒ externally



Dr. Stefan Diederichs
(Independent verifier appointed by SVR)

Product

Product description / Product definition

This EPD describes High-pressure decorative compact
laminates according to /EN 438-4/ (Compact HPL,
thickness ≥ 2 mm) with a density of at least 1350
kg/m³.

High-pressure decorative compact laminates are
characterised by their aesthetic qualities, strength,
durability and functional performance. Compact HPL
sheets are available in a wide variety of colours,
patterns and surface finishes. They are resistant to
wear, impact, scratching, moisture, heat, staining and
light and possess good hygienic and -antistatic
properties. Compact HPL are easy to clean and
maintain.

Compact HPL can be glued, riveted or screwed on
wooden or metallic substructures or anchored in

mechanical fastening brackets to be used in invisible
mounting systems.

Dimensions:

Length: up to 5600 mm
Width: up to 2200 mm

Thickness $2 \leq t < 40$ mm (Compact HPL, /EN 438-4/)
A large number of HPL manufacturing plants are
certified to /ISO 9001/ and/or /ISO 14001/.

Product according to the /CPR/ based on a hEN:

For the placing on the market of HPL Composite
Panels in the EU/EFTA (with the exception of
Switzerland) Regulation (EU) No. 305/2011 (/CPR/)
applies. HPL Composite Panels needs a Declaration of

Performance taking into consideration /EN 438-7/ and the CE-marking. For the application and use the respective national provisions apply.

Application

High-pressure decorative compact laminates can be used for private and -residential housing, hospitals and laboratories, public buildings, -railway stations, airport terminals/infrastructure, transportation, -hotels, education, retail and commercial buildings, sport & recreation centers and industrial buildings.

The performance properties of compact HPL make them suitable for use in a wide variety of interior applications such as: wall cladding, railing infill panels, furniture, tables, desks, column cladding and lab equipment, cubicles, ceilings, window sills, worktops, counter tops, wash basins, etc.

Technical Data

An extract of the technical properties of Compact HPL according to EN 438 part 4 is given in the following tables. For general purpose Compact HPL used in products without flame retardants, the following properties are given.

Constructional data

Name	Value	Unit
Gross density	≥ 1350	kg/m ³
Resistance to abrasion (IP) acc. to /EN 438/	≥ 150	U
Resistance to scratches acc. to /EN 438/	≥ 2	Degree
Flexural strength acc. to EN 483	≥ 80	N/mm ²
Modulus of elasticity acc. to /EN 438/	≥ 9000	N/mm ²
Light resistance acc. to /EN 438/	≥ 4	-
Dimensional deviation : Thickness tolerance	± 0.4	mm

Dimensional deviation: Length and width	+10/-0	mm
---	--------	----

- Performance data of HPL Composite Panels in accordance with the Declaration of Performance (DoP) with respect to its Essential Characteristics according to /EN 438-7/ apply.
- Voluntary data: /EN 438-4/

Base materials / Ancillary materials

More than 60 % of the Compact HPL consists of paper, and the remaining 30 to 40 % consists of cured phenol resin for core layers and melamine resin for the surface layer. Compact HPL is produced in a high-pressure process. Papers are impregnated with thermosetting resins and pressed together under simultaneous application of heat (temperature > 120 °C) and high specific pressure (≥ 5 MPa). This method produces a homogeneous, nonporous material with a density ≥ 1350 kg/m³.

Compact Laminates typically have two decorative sides.

For packaging the materials cardboard, wood/wooden pallets and polyethylene film are used.

Reference service life

Due to the wide range of applications no single reference service lifetime can be established. For information, the service life in standard applications can range from 20 to 50 years (ICDLI aisbl suggestion based on expert judgment).

LCA: Calculation rules

Declared Unit

The declared unit is 1 m² of Compact HPL with 8 mm thickness and a density of at least 1350 kg/m³. The declared unit refers to the Compact HPL products manufactured with phenolic impregnated kraft paper core and melamine impregnated decor paper. Special decors, fire retardants or alternative core production technologies are not included. The declared unit refers to the average Compact HPL products manufactured by ICDLI aisbl members (weighted average).

Declared unit

Name	Value	Unit
Declared unit	1	m ²
Grammage	10.8	kg/m ²
Conversion factor to 1 kg	0.0926	-

System boundary

Type of EPD: Cradle-to-gate with options.

Considered product stages:

- Production of pre-products (e.g. resin ingredients and papers), extraction of energy carriers, raw material transportation, manufacture of product and packaging

materials are declared in the modules A1-A3. Modules A1-A3 also include the manufacturing and supply of energy.

- The scenario for the transport of the product to the construction site is declared in module A4.
- The end-of-life scenarios include transportation to the waste processing and disposal (C2), emissions and energy requirements of combustion (C3; in case of scenario 1) and landfilling process (C4; in case of scenario 2). Credits for electricity and thermal energy, which result from energy recovery in modules C3 and C4, are declared in module D.
- The CO₂ incorporation is taken into account. The C-balance is closed due to consideration of biotic CO₂ emissions according to the incorporation on input side.

The data collected by the manufacturers is based on yearly production amounts. The production data refers to the yearly consumption in 2016.

were created according to /EN 15804/ and the building context, respectively the product-specific characteristics of performance, are taken into account. GaBi ts serves as background database for the calculation /Gabi ts/.

Comparability

Basically, a comparison or an evaluation of EPD data is only possible if all the data sets to be compared

LCA: Scenarios and additional technical information

The following technical information is a basis for the declared modules. This information can also be used for developing specific scenarios in the context of a building assessment for modules that are not declared (MND).

Transport to the building site (A4)

Name	Value	Unit
Transport distance	100	km
Capacity utilisation (including empty runs)	70	%
Gross density of products transported	1350	kg/m ³
Capacity utilisation volume factor	1	-

Packaging material:

81 g polyethylene film, 52 g cardboard, 600 g wood (from pallets) proportional per 1 m² HPL compact product.

End of life (C2-C4)

The transport to waste processing (module C2) is assumed to be 50 km. This scenario is valid for both EoL scenarios.

Name	Value	Unit
Collected separately	10.8	kg
Energy recovery	10.8	kg
Landfilling	10.8	kg

Reuse, recovery and/or recycling potentials (D), relevant scenario information

Scenario 1: Module D/1 includes the potential benefits in form of energy recovery of the incineration process C3/1 (incineration of HPL compact). A waste incineration plant with R1-value > 0.6 is assumed. Scenario 2: Landfilling with potential benefits in D/2 by use of landfill gas for electricity generation. Effort for landfilling process in C4/2.

LCA: Results

The following tables display the environmental relevant results according to /EN 15804/ for 1 m² HPL compact. The two End-of-Life Scenarios are represented in modules C2 to C4 and D. Scenario 1 reflects the thermal treatment of HPL compact with energy recovery. Scenario 2 shows the environmental results in case of disposal on landfill.

DESCRIPTION OF THE SYSTEM BOUNDARY (X = INCLUDED IN LCA; MND = MODULE NOT DECLARED)

PRODUCT STAGE			CONSTRUCTION PROCESS STAGE		USE STAGE							END OF LIFE STAGE				BENEFITS AND LOADS BEYOND THE SYSTEM BOUNDARIES
Raw material supply	Transport	Manufacturing	Transport from the gate to the site	Assembly	Use	Maintenance	Repair	Replacement	Refurbishment	Operational energy use	Operational water use	De-construction demolition	Transport	Waste processing	Disposal	Reuse-Recovery-Recycling-potential
A1	A2	A3	A4	A5	B1	B2	B3	B4	B5	B6	B7	C1	C2	C3	C4	D
X	X	X	X	MND	MND	MND	MND	MND	MND	MND	MND	MND	X	X	X	X

RESULTS OF THE LCA - ENVIRONMENTAL IMPACT: 1 m² HPL compact, thickness 8.0 mm (10.8 kg/m²)

Parameter	Unit	A1-A3	A4	C2	C3/1	C3/2	C4/1	C4/2	D/1	D/2
GWP	[kg CO ₂ -Eq.]	3.12E+1	7.31E-2	4.76E-2	1.16E+1	0.00E+0	0.00E+0	9.24E+0	-5.36E+0	-4.08E-1
ODP	[kg CFC11-Eq.]	3.30E-8	2.09E-14	1.36E-14	4.31E-12	0.00E+0	0.00E+0	1.90E-12	-1.07E-10	-1.81E-11
AP	[kg SO ₂ -Eq.]	5.42E-2	1.58E-4	1.10E-4	6.40E-3	0.00E+0	0.00E+0	2.98E-3	-8.66E-3	-1.17E-3
EP	[kg (PO ₄) ₃ -Eq.]	1.02E-2	3.41E-5	2.39E-5	1.59E-3	0.00E+0	0.00E+0	3.66E-3	-9.03E-4	-1.06E-4
POCP	[kg ethene-Eq.]	7.41E-3	-5.28E-5	-3.78E-5	4.14E-4	0.00E+0	0.00E+0	2.31E-3	-8.02E-4	-7.45E-5
ADPE	[kg Sb-Eq.]	1.12E-5	2.26E-9	1.47E-9	1.93E-7	0.00E+0	0.00E+0	1.60E-7	-1.08E-6	-1.63E-7
ADPF	[MJ]	471.00	1.02	0.66	4.75	0.00	0.00	11.10	-74.10	-4.36

Caption: GWP = Global warming potential; ODP = Depletion potential of the stratospheric ozone layer; AP = Acidification potential of land and water; EP = Eutrophication potential; POCP = Formation potential of tropospheric ozone photochemical oxidants; ADPE = Abiotic depletion potential for non-fossil resources; ADPF = Abiotic depletion potential for fossil resources

RESULTS OF THE LCA - RESOURCE USE: 1 m² HPL compact, thickness 8.0 mm (10.8 kg/m²)

Parameter	Unit	A1-A3	A4	C2	C3/1	C3/2	C4/1	C4/2	D/1	D/2
PERE	[MJ]	279.20	0.00	0.00	116.68	0.00	0.00	0.85	-14.50	-2.44
PERM	[MJ]	123.80	0.00	0.00	-116.00	0.00	0.00	0.00	0.00	0.00
PERT	[MJ]	403.00	0.00	0.00	0.68	0.00	0.00	0.85	-14.50	-2.44
PENRE	[MJ]	401.60	1.02	0.67	95.66	0.00	0.00	11.50	-90.80	-7.17
PENRM	[MJ]	93.40	0.00	0.00	-90.20	0.00	0.00	0.00	0.00	0.00
PENRT	[MJ]	495.00	1.02	0.67	5.46	0.00	0.00	11.50	-90.80	-7.17
SM	[kg]	4.25E-2	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
RSF	[MJ]	7.36E-1	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
NRSF	[MJ]	5.72E-1	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0	0.00E+0
FW	[m ³]	5.44E-1	5.96E-6	3.88E-6	4.43E-2	0.00E+0	0.00E+0	1.13E-3	-2.07E-2	-3.48E-3

Caption: PERE = Use of renewable primary energy excluding renewable primary energy resources used as raw materials; PERM = Use of renewable primary energy resources used as raw materials; PERT = Total use of renewable primary energy resources; PENRE = Use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM = Use of non-renewable primary energy resources used as raw materials; PENRT = Total use of non-renewable primary energy resources; SM = Use of secondary material; RSF = Use of renewable secondary fuels; NRSF = Use of non-renewable secondary fuels; FW = Use of net fresh water

RESULTS OF THE LCA – OUTPUT FLOWS AND WASTE CATEGORIES:

1 m² HPL compact, thickness 8.0 mm (10.8 kg/m²)

Parameter	Unit	A1-A3	A4	C2	C3/1	C3/2	C4/1	C4/2	D/1	D/2
HWD	[kg]	3.79E-6	1.09E-10	7.09E-11	2.65E-9	0.00E+0	0.00E+0	4.46E-8	-2.28E-8	-2.90E-9
NHWD	[kg]	2.79E-1	5.79E-6	3.76E-6	4.12E-2	0.00E+0	0.00E+0	8.68E+0	-3.42E-2	-4.72E-3
RWD	[kg]	8.39E-3	1.19E-6	7.74E-7	2.80E-4	0.00E+0	0.00E+0	1.75E-4	-6.62E-3	-1.11E-3
CRU	[kg]	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MFR	[kg]	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
MER	[kg]	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
EEE	[MJ]	0.00	0.00	0.00	19.00	0.00	0.00	3.31	0.00	0.00
EET	[MJ]	0.00	0.00	0.00	44.30	0.00	0.00	0.00	0.00	0.00

Caption: HWD = Hazardous waste disposed; NHWD = Non-hazardous waste disposed; RWD = Radioactive waste disposed; CRU = Components for re-use; MFR = Materials for recycling; MER = Materials for energy recovery; EEE = Exported electrical energy; EEE = Exported thermal energy

The incorporation of CO₂ in packaging materials (paper, cardboard, wood) represents 2.9% of the GWP impact in module A1-A3.

References

/EN 438-4/

High-pressure decorative laminates (HPL) - Sheets

based on thermosetting resins (usually called

laminates) - Part 4: Classification and specifications for

compact laminates of thickness 2 mm and greater; EN 438-4: 2005

/EN 438-7/

High-pressure decorative laminates (HPL) - Sheets based on thermosetting resins (usually called laminates) - Part 7: Compact laminate and HPL composite panels for internal and external wall and ceiling finishes; EN 438-7:2005

/GaBi ts/

GaBi ts 8 dataset documentation for the software system and databases, LBP, University of Stuttgart and thinkstep, Leinfelden-Echterdingen, 2016 (<http://documentation.gabi-software.com/>)

/PCR Part A/

PCR - Part A: Calculation rules for the Life Cycle Assessment and Requirements on the Background Report, version 1.6, Institut Bauen und Umwelt e.V., www.bau-umwelt.com, 2017

/PCR Part B/

Part B: Requirements on the EPD for Laminates, 07/2014

/CPR/

Regulation (EU) No 305/2011 of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of

construction products and repealing Council Directive 89/106/EEC

/ISO 9001/

Quality management systems - Requirements

/ISO 14001/

Environmental management systems - Requirements with guidance for use

Institut Bauen und Umwelt

Institut Bauen und Umwelt e.V., Berlin(pub.): Generation of Environmental Product Declarations (EPDs);

General Principles

for the EPD range of Institut Bauen und Umwelt e.V. (IBU), 2013/04
www.ibu-epd.de

/ISO 14025/

DIN EN /ISO 14025:2011-10/, Environmental labels and declarations — Type III environmental declarations — Principles and procedures

/EN 15804/

/EN 15804:2012-04+A1 2013/, Sustainability of construction works — Environmental Product Declarations — Core rules for the product category of construction products

**Publisher**

Institut Bauen und Umwelt e.V.
Panoramastr. 1
10178 Berlin
Germany

Tel +49 (0)30 3087748- 0
Fax +49 (0)30 3087748- 29
Mail info@ibu-epd.com
Web www.ibu-epd.com

**Programme holder**

Institut Bauen und Umwelt e.V.
Panoramastr 1
10178 Berlin
Germany

Tel +49 (0)30 - 3087748- 0
Fax +49 (0)30 - 3087748 - 29
Mail info@ibu-epd.com
Web www.ibu-epd.com



thinkstep

**Author of the Life Cycle
Assessment**

thinkstep AG
Hauptstraße 111- 113
70771 Leinfelden-Echterdingen
Germany

Tel +49 711 341817-0
Fax +49 711 341817-25
Mail info@thinkstep.com
Web www.thinkstep.com



International Committee of the
Decorative Laminates Industry

Owner of the Declaration

ICDLI aisbl Headoffice:
Städelstraße 10
60596 Frankfurt am Main
Germany

Tel +49 69 2 71 05-31
Fax +49 69 23 98 37
Mail info@pro-kunststoff.de
Web www.icdli.com